

Technical data sheet: P-filament

Polypropylene (PP) is one of the most widely used plastics with a broad property profile. PP is one of the lightest materials and has excellent mechanical and chemical properties.

Material description

Trade name	P-filament
Manufacturer	PPprint GmbH
Polymer group	Thermoplastic polymer
Chemical name	Polypropylene copolymer
Use	Extrusion-based 3D printing

Suggested 3D print settings (nozzle diameter 0.4mm)

Nozzle temperature	200 - 220 °C
Bed temperature	20 °C (50 - 80 °C recommended for the first layer, 100 – 110 °C for non-destructive removal after completion)
Chamber temperature	not required
Bed modification	P-surface
Active fan cooling	recommended
Layer height	0.1 – 0.4 mm
Print speed	15 – 40 mm/s

Material properties

Melt temperature	137 °C	ASTM D3418
Melt Flow Rate ¹	19.3 g/10 min	ISO 1133
Melt Volume Rate ¹	25.7 cm ³ /10 min	ISO 1133
Density	0.9 g/cm ³	ISO 1183
Odor	odorless	-

¹ Test conditions: T = 210 °C; m = 5.0 kg

Mechanical properties: Tensile test

All specimens were punched out of printed square tubes consisting of two shells, which were 3D printed with a Raise Pro 3D printer and applying the following printing conditions:

Nozzle temperature: 210 °C;

Bed temperature: 70 °C;

Chamber temperature: 70 °C;

Printing speed: 30 mm/s.

90°



punched dog bone: S 3A with an orientation of 90° to the nozzle movement direction

0°



punched dog bone: S 3A with an orientation of 0° to the nozzle movement direction

E-Modul (MPa)	640 ± 20	660 ± 10
Yield strength (MPa)	18.1 ± 0.1	19.6 ± 0.3
Tensile strength (MPa)	18.7 ± 0.3	35.1 ± 0.6
Strain at break (%)	> 600	> 600

Certifications/ approvals*

PPprint GmbH

Gottlieb-Keim-Straße 60

D-95448 Bayreuth

Regulation EU Nr. 10/2011 Union Guidelines on Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Europe)

FDA Food and Drug administration approval (USA)

* These data are generated using information obtained from the raw material suppliers.

Filament specification

Diameter 1.75	1.75 ± 0.10 mm	PPprint
Diameter 2.85	2.85 ± 0.10 mm	PPprint
Ovality	0.05	PPprint
Netto weight on spool	600 g ± 5%	PPprint

Annotation

The data and properties presented here are averages of a standard batch. The 3D printed square tubes from which the specimens were punched out were produced in Slic3r version 1.3.0.

Disclaimer

Acceptance of any technical information or assistance contained herein is at your own risk. PPprint GmbH makes no warranty with respect to or based on this information. PPprint GmbH is not liable for the use of this information or the mentioned products, processes or devices. It is your sole responsibility to determine their suitability and completeness for your individual application, for the protection of the environment as well as for the health and safety of your employees and buyers of your products. PPprint GmbH makes no warranty as to the marketability or suitability of the products and nothing herein constitutes a waiver of PPprint's Terms of Sale. Specifications are subject to change without notice.

Version: 1.001

Date: 12.02.2019

PPprint GmbH

Gottlieb-Keim-Straße 60

D-95448 Bayreuth

Seite 3 von 3